

Duplex Delfos Plus C1S reverso Kraft

Technical Specifications

Ítems español	Ítems inglés	Unidad	Método de Prueba	Standard						
Gramaje	Grammage	g/m²	GB/T451.2 ISO536	200	230	250	270	300	325	360
Espesor	Thickness	µm	GB/T451.3 ISO534	300	350	390	430	485	540	590
Humedad	Moisture	%	GB/T462 ISO287				7.5			
Rigidez Taber	CD	mN·m	GB/T22364 ISO2493	3.90	6.30	8.40	10.6	14.3	18.1	22.6
				3.30	5.40	7.10	9.00	12.2	15.4	19.2
	MD			7.20	11.8	15.8	20.0	27.0	34.2	42.8
				6.10	10.0	13.4	17.0	23.0	29.1	36.4
Brillo	Brightness (D65)	%	GB/T7974 ISO2470	78						
Rugosidad de Superficie - Cara	PPS Surface Roughness - Top	µm	GB/T22363 ISO8791	2.0						
Rugosidad de Superficie - Dorso	Bendtsen Surface Roughness - Back	mL/min	GB/T22363 ISO8791-2	2000						
Fuerza de Unión entre Capas	Ply Bond	J/m²	GB/T26203 TAPPI 569	100						
Brillo - Cara	Gloss - Top	%	GB/T8941 ISO8254	30						
Absorción de Agua - Cara/Dorso (3min)	Cobb - Top/Back (3min)	g/m²	GB/T1540 ISO535	60						
Infiltración	Método de Distancia (Distance Method)	mm	GB/T31905	5.0						
	Método de Pesaje (Weighing Method)	kg/m²	GB/T31905	1.5						
Agente de Blanqueo Óptico	Optical Brightening Agent	-	GB31604.47	Negativo						